

Nick Papa

Color	Nick Papa
Size	7 x 48 in
Thickness	2 mm
Wearlayer Thickness	12 mil
Textures	Deep Wood Embossed
Edge	Micro-Beveled
Finish	Matte with TuffCoat
Install	Glue Down

Symbols	Test	Results
	ASTM F2421 Dimensional Tolerance	Pass
	ASTM F2199 Dimensional Stability	Pass
	ASTM F970 Static Load	0.000 inch (Pass)
	ASTM F1514 Heat Stability	5.0 (Pass)
	ASTM F1515 Light Stability	4.5 (Pass)
	ASTM F925 Chemical Resistance	Pass
	ASTM F386 Average Thickness	0.083 inch
	ASTM F410 Wear Layer Thickness	0.0112 inch/11.2 mil
	ASTM F3261 Thickness Swell	0%
	ISO 24337 Geometrical Characteristics	Pass
	US EPA 3052:1996 Heavy Metal Content	Not Detected
	Hexavalent Chromium (Cr VI)	Not Detected
	Soluble elements	Not Detected
	Phthalate Content	Not Detected
	ASTM F1914 ASTM F3261	
	Residual Indentation at 75 lbs.	0.000 inch (Pass)
	Surface Integrity	No puncture through layer/décor into rigid core
Size Options		
6"x36", 6"x48", 7"x48"		

LPT Plank

Size	7 x 48 in
Thickness	2 mm
Wearlayer Thickness	12 mil
Textures	Deep Wood Embossed
Edge	Straight
Finish	Matte with TuffCoat
Install	Glue Down

Symbols	Test	Results
 	ASTM F2421 Dimensional Tolerance ASTM F2199 Dimensional Stability ASTM F970 Static Load ASTM F1514 Heat Stability ASTM F1515 Light Stability ASTM F925 Chemical Resistance ASTM F386 Average Thickness ASTM F410 Wear Layer Thickness ASTM F3261 Thickness Swell ISO 24337 Geometrical Characteristics US EPA 3052:1996 Heavy Metal Content Hexavalent Chromium (Cr VI) Soluble elements Phthalate Content ASTM F1914 ASTM F3261 Residual Indentation at 75 lbs. Surface Integrity	Pass Pass 0.000 inch (Pass) 5.0 (Pass) 4.5 (Pass) Pass 0.083 inch 0.0112 inch/11.2 mil 0% Pass Not Detected Not Detected Not Detected Not Detected 0.000 inch (Pass) No puncture through layer/décor into rigid core
Size Options		
6" x 36", 6" x 48", 7" x 48"		